



Technical Data Sheet

ACS Material ZSM-23

Table of Contents

[1 – Characterizations](#)

[2 – Application Fields](#)

[3 – Storage](#)

Contact Information:

Manufacturer: ACS Material, LLC.

Address: 959 E Walnut St., Suite 100,

Pasadena, CA 91106, USA

Phone: (866)-227-0656

Fax: (781)-518-0284


E-Mail: contact@acsmaterial.com

Revision: 080924


1. Characterizations

	Type A	Type B	Type C	Type D
Length* (nm):	100-250	-	-	-
Diameter* (nm):	40-50	-	-	-
SiO₂/Al₂O₃ Molar Ratio:	~80	~20-35	~40-50	~55-70
Crystallinity:	>95%	≥90%	≥90%	≥90%

*These data are based on the SEM



Typical SEM Image of ACS Material ZSM-23, Type A



3. Application Fields

- 1) Catalyst
- 2) Lubricating Oil Hydroisomerization
- 3) Butene isomerization

4. Storage

Keep container tightly closed in a dry and well-ventilated place.

Disclaimer: ACS Material, LLC believes that the information in this Technical Data Sheet is accurate and represents the best and most current information available to us. ACS Material makes no representations or warranties either express or implied, regarding the suitability of the material for any purpose or the accuracy of the information contained within this document. Accordingly, ACS Material will not be responsible for damages resulting from use of or reliance upon this information.